

Color vs. Material Reference Guide

| Color Description, Name | Ref. # | Steel Gauge | | | Aluminum Gauge | | | | Initial Solar Reflectance | Thermal Emittance | Solar Reflectance Index (SRI) | Light Reflectance Value |
|---|--------|-------------|----|----|----------------|-------|-------|-------|---------------------------|-------------------|-------------------------------|-------------------------|
| | | 29 | 24 | 22 | 0.032 | 0.040 | 0.050 | 0.063 | | | | |
| Standard Colors | | | | | | | | | | | | |
| Classic Bronze | 1 | | * | * | * | * | * | * | 0.12 | 0.82 | 4 | 4.09 |
| Black | 2 | | * | | * | * | * | * | 0.05 | 0.86 | -2 | 5 |
| Medium Bronze | 3 | | * | * | * | * | * | * | 0.33 | 0.86 | 34 | 11 |
| Chocolate Brown | 4 | | * | | * | * | * | * | 0.26 | 0.86 | 24 | 7 |
| Concord Cream | 5 | | * | | * | * | * | * | 0.65 | 0.85 | 78 | 62.13 |
| Sandstone | 6 | | * | * | * | * | * | * | 0.57 | 0.85 | 66 | 49.76 |
| Redwood | 7 | * | * | | * | * | * | * | 0.24 | 0.84 | 22 | 5.54 |
| Mission Red | 8 | * | * | | * | * | * | * | 0.41 | 0.86 | 45 | 15 |
| Sierra Tan | 9 | * | * | | * | * | * | * | 0.48 | 0.86 | 54 | 32 |
| Ascot White | 10 | | * | | * | * | * | * | 0.64 | 0.86 | 83 | 68 |
| Forest Green | 11 | * | * | | * | * | * | * | 0.28 | 0.85 | 27 | 10 |
| Patina Green | 12 | | * | | * | * | * | * | 0.46 | 0.86 | 51 | 24 |
| Dove Grey | 13 | | * | | * | * | * | * | 0.5 | 0.83 | 55 | 35.18 |
| Siam Blue | 14 | | * | | * | * | * | * | 0.34 | 0.85 | 35 | 18.94 |
| Rawhide | 15 | | * | | * | * | * | * | 0.55 | 0.85 | 64 | 40.02 |
| Rocky Grey | 16 | * | * | | * | * | * | * | 0.29 | 0.86 | 28 | 14 |
| Regal Blue | 18 | | * | | * | * | * | * | 0.27 | 0.86 | 26 | 10 |
| Teal | 19 | | * | | * | * | * | * | 0.3 | 0.85 | 30 | 10.56 |
| Slate Grey | 20 | * | * | * | * | * | * | * | 0.4 | 0.83 | 42 | 17.13 |
| Slate Blue | 21 | | * | | * | * | * | * | 0.31 | 0.86 | 31 | 18.32 |
| Boysenberry | 25 | | * | | * | * | * | * | 0.28 | 0.86 | 28 | 8 |
| Bone White | 26 | * | * | * | * | * | * | * | 0.74 | 0.86 | 90 | 76 |
| Hartford Green | 27 | | * | | * | * | * | * | 0.25 | 0.85 | 23 | 5.03 |
| Hemlock Green | 30 | | * | | * | * | * | * | 0.3 | 0.86 | 30 | 17.18 |
| Charcoal Grey | 62 | | * | | * | * | * | * | 0.29 | 0.82 | 27 | 10.01 |
| 55% Al-Zn Alloy Coated Steel with Acrylic Coating | 97 | | * | | | | | | 0.68 | 0.14 | 58 | |
| Mill Finish-Aluminum | 99 | | | | * | * | * | * | — | — | — | — |
| Matte Finish | | | | | | | | | | | | |
| Char Brown | 29 | * | | | * | * | | | 0.24 | 0.84 | 20 | 4.34 |
| Matte Black | 32 | | * | | * | * | | | 0.09 | 0.84 | 2 | 3.7 |
| Ash Grey | 33 | | * | | * | * | | | 0.5 | 0.86 | 57 | 37 |
| Thunder Grey | 34 | | * | | * | * | | | 0.26 | 0.86 | 25 | 13 |
| Almond | 36 | | * | | * | * | * | | 0.64 | 0.86 | 76 | 60 |
| Anchor Grey | 37 | | * | | * | * | | | 0.39 | 0.84 | 41 | 17.77 |
| Premium Finish | | | | | | | | | | | | |
| Brite Red | 17 | | * | | * | * | * | | 0.41 | 0.83 | 43 | 8.22 |
| Coppertone | 23 | | * | | * | * | | | 0.52 | 0.83 | 58 | 24.54 |
| Antique Patina | 24 | | * | | * | * | * | | 0.26 | 0.85 | 24 | 14.33 |
| Silversmith | 28 | | * | * | * | * | * | | 0.54 | 0.82 | 60 | 31.03 |
| Champagne | 31 | | * | | * | * | * | | 0.59 | 0.82 | 67 | 38.46 |
| Titanium | 35 | | * | | * | * | * | | 0.59 | 0.84 | 68 | 38.63 |
| Clear Satin Anodized | 70 | | | | * | * | * | * | 0.77 | 0.7 | 92 | |
| Dark Bronze Anodized | 71 | | | | * | * | | | 0.15 | 0.77 | 6 | |
| Advanta Americana Classic (stamped shingles) | | | | | | | | | | | | |
| Asheland Slate | AS | * | | | | | | | 0.44 | 0.83 | 48 | |
| Baja Slate | BS | * | | | | | | | 0.27 | 0.83 | 25 | |
| Beech Tree | BT | * | | | | | | | 0.38 | 0.84 | 40 | |
| Deep Granite | DG | * | | | | | | | 0.25 | 0.83 | 22 | |
| Quarry Slate | QS | * | | | | | | | 0.31 | 0.84 | 31 | |
| Rocky Cliff | RC | * | | | | | | | 0.29 | 0.83 | 27 | |
| Shaded Spruce | SS | * | | | | | | | 0.25 | 0.83 | 22 | |
| Weathered Stone | WN | * | | | | | | | 0.27 | 0.83 | 25 | |
| Willow Slate | WS | * | | | | | | | 0.3 | 0.83 | 29 | |